



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G01N 33/30, 19/02	A1	(11) International Publication Number: WO 99/45381 (43) International Publication Date: 10 September 1999 (10.09.99)
<p>(21) International Application Number: PCT/US99/04839</p> <p>(22) International Filing Date: 4 March 1999 (04.03.99)</p> <p>(30) Priority Data: 09/033,625 4 March 1998 (04.03.98) US</p> <p>(71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 1900 East Linden Avenue, P.O. Box 710, Linden, NJ 07036 (US).</p> <p>(72) Inventors: HOFFMAN, Charles, F.; 732 Mill Lane, Neshanic Station, NJ 08853 (US). MENY, Emil, J.; 4 Sheffield Road, Summit, NJ 07901 (US). COLBY, Patrick, J.; 605 Willow Avenue, Piscataway, NJ 08854 (US). NIBERT, Roger, K.; 105 Main Street, Hampton, NJ 08827 (US).</p> <p>(74) Agent: GREELEY, Paul, D.; Ohlandt, Greeley, Ruggiero & Perle, L.L.P., 9th floor, One Landmark Square, Stamford, CT 06901-2682 (US).</p>		<p>(81) Designated States: CA, CN, JP, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: CLUTCH FRICTION TEST FOR MOTORCYCLE LUBRICANTS</p> <p>(57) Abstract</p> <p>A modified SAE No. 2 friction machine is used to evaluate the clutch friction properties of motorcycle lubricants in a process comprising measuring the torque after a break-in period at three temperature points within the ranges 30°–60 °C, 70°–90 °C and 110°–150 °C over a 10 second period while the speed of the motor driving the clutch plates varies from 0–300 rpm and the clutch plate pressure is held at 50 psi.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CLUTCH FRICTION TEST FOR MOTORCYCLE LUBRICANTS

This invention relates to a test procedure for evaluating the clutch friction properties of motorcycle lubricants. More particularly, this invention relates to an effective test procedure for the friction properties of such lubricants utilizing a modified SAE No. 2 friction machine.

In a typical motorcycle, a common sump lubricates the engine, transmission and wet clutch. Such universal lubricating fluids as used in motorcycles, therefore, must have a balance of both desirable friction properties and lubricity properties. Heretofore, there has been no standardized test which can effectively evaluate friction properties of motorcycle lubricants as to enable the design and formulation of such lubricants to meet requirements of manufacturers. The present invention permits one to evaluate the effect of lubricant additives on friction characteristics of motorcycle lubricants.

The SAE No. 2 machine has been used to evaluate friction properties of various fluids other than motorcycle lubricants and representative disclosures are found in U.S. Patent 5,484,543, January 16, 1996 to Chandler et al., U.S. Patent 5,441,656, August 15, 1995 to Ohtani et al. and a publication entitled "SAE No. 2 Clutch Friction Test Machine Test Procedure", published as SAE J286, November, 1983.

In accordance with the present invention there has been discovered a method for measuring the clutch friction properties of a motorcycle universal lubricant used for lubrication of the motorcycle's engine, transmission and wet clutch which comprises introducing a motorcycle lubricant test fluid into a modified SAE No. 2 test machine as shown in the Figure and measuring the coefficient of friction of the fluid according to the following procedure and conditions:

- (A) stabilizing the fluid by operating the machine motor at 100 rpm, applying a pressure of 25 psi to the clutch plates and maintaining the

fluid at a temperature of 30° - 60°C, such as 40°C, for at least 10 minutes;

5 (B) while maintaining the fluid at 30° - 60°C, such as 40°C, increasing the motor speed to 300 rpm over a 5 second period then decreasing the motor speed over a 5 second period to 0 rpm and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;

10 (C) repeating step (B) twice;

(D) stabilizing the fluid at 70° - 90°, such as 80°C, maintaining the motor at 100 rpm and maintaining the pressure at 50 psi for at least 10 minutes;

15

(E) while maintaining the fluid at 70° - 90°, such as 80°C, increasing the motor speed to 300 rpm over a 5 second period then decreasing the motor speed to 0 rpm over a 5 second period and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;

20

(F) repeating step (E) twice;

25 (G) stabilizing the fluid at 110° - 150°C, such as 120°C, maintaining the motor speed at 100 rpm and maintaining the pressure at 50 psi for at least 10 minutes;

30

(H) while maintaining the fluid at 110° - 150°C, such as 120°C, increasing the motor speed to 300 rpm over a 5 second period then decreasing the motor speed to 0 rpm over a 5 second period and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;

- (I) repeating step (H) twice;
- 5 (J) from the data of steps (C), (F) and (I), calculating the coefficient of friction at any temperature used in the preceding steps and at any clutch plate speed according to the equation $\mu = T/F \cdot N \cdot R$ where T is torque in inch-pounds, F is force applied in pounds, N is the number of active friction surfaces and R is friction plate radius in inches, said calculation being done to evaluate the operational validity of the test system and
- 10 equipment;
- (K) conducting a break-in period by maintaining the fluid at for 1 to 4 hours at 110° - 150°C, such as 120°C, 100 rpm and 50 psi;
- 15 (L) repeating steps (H) and (I);
- (M) stabilizing the fluid at 70° - 90°C, such as 80°C, 100 rpm and 50 psi for at least 10 minutes;
- 20 (N) repeating steps (E) and (F);
- (O) stabilizing the fluid at 30° - 60°C, such as 40°C, 100 rpm and 50 psi for at least 10 minutes;
- 25 (P) repeating steps (B) and (C); and
- (Q) from the data of steps (L), (N) and (P), calculating the coefficient of friction for the fluid at any clutch plate speed and at any temperature according to the equation: $\mu = T/F \cdot N \cdot R$ where T is torque in inch-pounds, F is force applied in pounds, N is number of active friction
- 30 surfaces and R is friction plate radius in inches, said calculation being done to evaluate the friction properties of the fluid tested.

A test procedure in accordance with this invention is carried out at temperatures preferably of 40°C, 80°C and 120°C, but these temperatures may be expanded to ranges, respectively, of 30-60°C, 70-90°C and 110-150°C. But the same
5 three temperatures should be used in both phases of the test, i.e., the same three temperatures used in steps (A) through (I) should also be used in steps (K) through (P). Thus the step (K) temperature should be the same as the step (H) temperature, the step (M) temperature should be the same as the step (E) temperature and the step (O) temperature should be the same as the step (B) temperature. The coefficient of
10 friction may be calculated for any of the three temperatures used in the series of steps comprising the test.

When data is measured over the 10 second periods referred to above, the data is continuously collected during this time period. Coefficient of friction calculations
15 are made at any given clutch plate speed and at one of the three temperatures in the series of steps.

THE DRAWING

The Figure depicts schematically a modified SAE No. 2 machine which is
20 used in accordance with this invention. The parts of the machine as labeled in the Figure are identified in Table I below.

TABLE I

Legend	Part Description
A	Clutch pack housing
B	Spacer inside housing
C	Friction plates
D	Test fluid reservoir
E	Steel clutch plate
F	Air piston
G	Load cell for torque measurement
H	AC motor (static motor) 1.5 KW
I	Speed reducer
J	Motor shaft extension
K	Worm gear
L 1	3600 rpm AC motor
L 2	300 rpm AC motor and Speed Measuring Device
M	Flywheel
TC-1	Thermocouple bulk fluid

The SAE No. 2 friction machine used in this invention was fitted with adapters
 5 to accept Yamaha and Honda clutch plates. Friction and steel plates from a Yamaha XT-225 (223 cc) four stroke motorcycle were used for the lubricants tested in Table II.

The test profile consists of a pre break-in and a post break-in period. Each
 break-in period has three stabilizing stages at 40°C or, more broadly, 30-60°C, 80°C
 10 or, more broadly, 70-90°C and 120°C or, more broadly, 110-150°C. In between the pre and post break-in periods is a one hour break-in period at maximum test temperature of preferably 120°C or, more broadly, 110-150°C, a maximum test pressure of 50 psi and a maximum test speed of 300 rpm. Three speed ramps from 0 to maximum test speed and back to 0 are completed at each temperature. The actual
 15 data used to determine the friction coefficient of test lubricants for the purpose of evaluating the fluid's performance is taken during the post break-in 110° - 150°C period, i.e., steps (K) - (Q). Data taken during the initial three temperature phases, the test procedure, i.e., steps (A) - (J) as recited above is for the purpose of evaluating the operational validity of the test system and is an essential part of the test procedure.
 20 Friction coefficient of the test lubricants is calculated from the measured torque values

generated during this portion of the test. A friction trace is developed by plotting friction coefficient vs. clutch plate speed. By comparing the friction traces of test lubricants one is able to predict whether the lubricant will exhibit acceptable or poor clutch performance using a particular clutch material. The effect of additives on clutch performance can also be measured by comparing the test results of different oils.

Table II set forth below shows the results for three commercial lubricants which were tested in accordance with this invention. The μ , coefficient of friction is reported below for 120°C and a clutch plate speed of 0.4 m/second.

TABLE II

Commercial Lubricant	Start Value	Initial Slope	μ at 0.4m/s	Final Slope
A	0.0880	0.0824	0.0950	-0.0120
B	0.1050	0.0253	0.1560	-0.0070
C	0.1250	0.2690	0.1800	0.0090

- 15 Lubricant A: Honda Ultra GP Motorcycle Oil SAE 10W-40
Lubricant B: Yamalube4 4-Cycle Engine Oil SAE 10W-30
Lubricant C: 10W-30 Motorcycle oil based on "Paratemps 850" additive package, Exxon Chemical Co., Paramins Division

What is claimed is:

1. A method for measuring the clutch friction properties of a motorcycle universal lubricant used for lubrication of the motorcycle's engine, transmission and wet clutch which comprises introducing a motorcycle lubricant test fluid into a modified SAE No. 2 test machine as shown in the Figure and measuring the coefficient of friction of the fluid according to the following procedure and conditions:
 - 10 (A) stabilizing the fluid by operating the machine motor at 100 rpm applying a pressure of 25 psi to the clutch plates and maintaining the fluid at a temperature of 30° - 60°C for at least 10 minutes;
 - (B) while maintaining the fluid at 30° - 60°C, increasing the motor speed to 15 300 rpm over a 5 second period then decreasing the motor speed over a 5 second period to 0 rpm and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;
 - 20 (C) repeating step (B) twice;
 - (D) stabilizing the fluid at 70° - 90°C, maintaining the motor at 100 rpm and maintaining the pressure at 50 psi for at least 10 minutes;
 - 25 (E) while maintaining the fluid at 70° - 90°C, increasing the motor speed to 300 rpm over a 5 second period then decreasing the motor speed to 0 rpm over a 5 second period and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;
 - 30 (F) repeating step (E) twice;

- WO 99/43381
- (G) stabilizing the fluid at 110° - 150°C, maintaining the motor speed at 100 rpm and maintaining the pressure at 50 psi for at least 10 minutes;
- 5 (H) while maintaining the fluid at 110° - 150°C, such as 120°C, increasing the motor speed to 300 rpm over a 5 second period then decreasing the motor speed to 0 rpm over a 5 second period and continuously measuring the clutch plate speed and the torque during said 10 second period while maintaining the pressure at 50 psi;
- 10 (I) repeating step (H) twice;
- (J) from the data of steps (C), (F) and (I), calculating the coefficient of friction at any temperature used in the preceding steps and at any clutch plate speed according to the equation $\mu = T/F \cdot N \cdot R$ where T is torque in inch-pounds, F is force applied in pounds, N is the number of active friction surfaces and R is friction plate radius in inches, said calculation being done to evaluate the operational validity of the test system and equipment;
- 15 (K) conducting a break-in period by maintaining the fluid at for 1 to 4 hours at 110° - 150°C, such as 120°C, 100 rpm and 50 psi;
- (L) repeating steps (H) and (I);
- 20 (M) stabilizing the fluid at 70° - 90°C, such as 80°C, 100 rpm and 50 psi for at least 10 minutes;
- (N) repeating steps (E) and (F);
- 25 (O) stabilizing the fluid at 30° - 60°C, such as 40°C, 100 rpm and 50 psi for at least 10 minutes;
- 30

(P) repeating steps (B) and (C); and

(Q) from the data of steps (L), (N) and (P), calculating the coefficient of friction for the fluid at any clutch plate speed and at any temperature used in the preceding steps according to the equation: $\mu = T/F \cdot N \cdot R$ where T is torque in inch-pounds, F is force applied in pounds, N is number of active friction surfaces and R is friction plate radius in inches, said calculation being done to evaluate the friction properties of the fluid tested.

5
10

2. The method of claim 1 wherein the temperature used in steps (A), (B) and (O) is 40°C, the temperature used in steps (D), (E) and (M) is 80° and the temperature used in steps (G), (H) and (K) is 120°C.

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G01N33/30 G01N19/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 441 656 A (OHTANI HIROKO ET AL) 15 August 1995 cited in the application see column 13, line 19 - column 15, line 34 ---	1,2
A	US 5 484 543 A (CHANDLER JOHN E ET AL) 16 January 1996 cited in the application see column 48, line 29 - column 51, line 46 ---	1,2
A	US 5 320 768 A (GUTIERREZ ANTONIO ET AL) 14 June 1994 see column 30, line 25 - column 31, line 55 --- -/--	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

17 June 1999

Date of mailing of the international search report

28/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Brison, O

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/04839

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 97 14773 A (EXXON CHEMICAL PATENTS INC) 24 April 1997 see page 19, line 22 - page 20, line 10 -----	1,2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/04839

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5441656	A	15-08-1995	US 5372735 A	13-12-1994
			AU 685551 B	22-01-1998
			AU 1165795 A	17-08-1995
			CA 2142056 A	11-08-1995
			DE 69502222 D	04-06-1998
			DE 69502222 T	13-08-1998
			EP 0670362 A	06-09-1995
			JP 8053682 A	27-02-1996
<hr/>				
US 5484543	A	16-01-1996	US 5395539 A	07-03-1995
			AT 100133 T	15-01-1994
			AU 635229 B	18-03-1993
			AU 4503489 A	14-05-1990
			CA 2001381 A	24-04-1990
			DE 68912307 D	24-02-1994
			DE 68912307 T	05-05-1994
			EP 0394422 A	31-10-1990
			JP 3502114 T	16-05-1991
			KR 146707 B	01-08-1998
			WO 9004625 A	03-05-1990
<hr/>				
US 5320768	A	14-06-1994	DE 68907288 T	21-10-1993
			EP 0353854 A	07-02-1990
			JP 2060996 A	01-03-1990
			JP 2807902 B	08-10-1998
<hr/>				
WO 9714773	A	24-04-1997	US 5750476 A	12-05-1998
			AU 7433896 A	07-05-1997
			CA 2226977 A	24-04-1997
			EP 0877784 A	18-11-1998